




288mm 388mm








Specifications

| No | minal Voltage | 12V | | | |
|-------------------------------|-------------------------------|---------------------------|--|--|--|
| Rated Capacity (20 hour rate) | | 160AH | | | |
| | Total Height (with terminals) | 241mm(9.49inches) | | | |
| Dimension | Height | 241mm(9.49inches) | | | |
| | Length | 484mm(19.06inches) | | | |
| | Width | 171mm(6.73inches) | | | |
| | Weight | Approx.45.7kg (100.54Ibs) | | | |


Discharge characteristics $77^{\circ}F(25^{\circ}C)$



Characteristics

| | 20 hour rate | 160AH | | | | |
|-------------------------------------------------|-----------------------------|----------------------|--|--|--|--|
| Capacity | 10 hour rate | 148AH | | | | |
| 77°F(25°C) | 5 hour rate | 136AH | | | | |
| | 1 hour rate | 96AH | | | | |
| Internal Resistance | Full charged | 3mΩ | | | | |
| Standard Terminal | M8 | • | | | | |
| Capacity affected by Temperature (20 hour rate) | 104℉(40℃) | 102% | | | | |
| | 77°F(25°C) | 100% | | | | |
| | 32°F(0°C) | 85% | | | | |
| | 5°F(-15°C) | 65% | | | | |
| Self-Discharge | Capacity aft | 91% | | | | |
| | Capacity aft | 82% | | | | |
| 77 °F (25°C) | Capacity aft | 64% | | | | |
| Max. Discharge Current 77°F (25°C) | 1500A (5s) | | | | | |
| Maximum Charge Current(A) | 32A | | | | | |
| Charging (Constant Voltage) | Cycle | 14.5V~14.9V/77℉(25℃) | | | | |
| | Float 13.6V~13.8V/77F(25°C) | | | | | |
| Temperature compensation | Cycle | -4mV/°C/cell | | | | |
| coefficient of charging voltage (mV/°C/cell) | Float | -3mV/°C/cell | | | | |

Duration of discharge vs. Discharge current



Constant Current Discharge Rating Amperes @ 77°F (25°C)

| Cut off voltage V/cell | 15M | 30M | 45M | 1H | 2Н | 3Н | 5H | 8Н | 10H | 12H | 20H | 24H |
|------------------------|-----|-----|-------|------|------|------|------|-------|-------|-------|------|------|
| 1.75V | 261 | 152 | 115.8 | 94.1 | 53.9 | 39.4 | 26.7 | 18.20 | 14.88 | 12.67 | 8.00 | 6.70 |

Note The above data are average values, and can be obtained with 3 charge/discharge cycles. These are not minimum values.

HGL BATTERIES